

# CERAN LT



Grease



**Extreme-pressure water resistant low temperature synthetic calcium sulfonate complex grease.**

## APPLICATIONS

**Multi purpose heavy duty water resistant grease.**  
**Low temperature applications in industry.**  
**Recommendation**

- **CERAN LT** is a synthetic heavy duty extreme pressure grease, specially designed for applications working under various temperature conditions.
- **CERAN LT** is pre-eminently suitable for lubrication of industrial, and 'heavy duty' off-road applications working in very low temperature environments.
- **CERAN LT** is also used as protection grease.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

## SPECIFICATIONS

- ISO 6743-9: L-XDDIB 1/2
- DIN 51 502: KP1/2N -40

## ADVANTAGES

**True multi purpose**  
**High loads**  
**Water resistant**  
**Low temperatures**  
**High temperatures**  
**Anti corrosion**

**No harmful substances**

- Thanks to its very sophisticated formula and use of synthetic base oil, **CERAN LT** performs well at very low as well as high temperatures.
- Excellent thermal stability. It regains its original texture after cooling to ambient temperature.
- Remarkable load resistance thanks to its naturally high extreme pressure and anti-wear properties.
- Extraordinary water resistance, no significant loss of consistency is observed even with high amounts of water entering the grease.
- Excellent anti-oxidation and anti-corrosion properties thanks to the very nature of the calcium sulfonates, also in the presence of sea water.
- **CERAN LT** does not contain lead, or other heavy metals considered harmful to human health and the environment.

TYPICAL CHARACTERISTICS	METHODS	UNITS	CERAN LT
Soap/thickener		-	Calcium sulfonate
NLGI grade	ASTM D 217/DIN 51 818	-	1 - 2
Color	Visual	-	Brown
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 40 to 150
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	280 - 310
Four ball weld load	ASTM D 2596	kgf	500
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0 - 0
Dropping point	IP 396/NFT 60 102C	°C	> 300
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	mm <sup>2</sup> /s (cSt)	80

Above characteristics are mean values given as an information.

**TOTAL LUBRIFIANTS**  
**Industrie & Spécialités**  
31-10-2007 (supersedes 21-12-2004)  
CERAN LT  
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.  
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser [www.quick-fds.com](http://www.quick-fds.com).