

ISOVOLTINE II X



Insulating

Inhibited insulating oil.

APPLICATIONS

Insulating oil

- ISOVOLTINE II X is an inhibited naphthenic mineral oil for transformers, rheostats and circuit breakers using mineral oils.

SPECIFICATIONS

International specifications

- IEC 60296: 2012
- BS EN 60296: 2012

ADVANTAGES

- Contains inhibitor to ensure a better resistance to oxidation.
- High insulating capability.
- Low viscosity for effective cooling.
- Very good low temperature properties.
- Absolutely no impurities such as dissolved gas, water or suspended solids.
- Does not contain DBDS.
- Does not contain PCB.

TYPICAL CHARACTERISTICS	METHODS	UNITS	ISOVOLTINE II X
Density at 20 °C	ISO 12185	kg/m ³	875
Viscosity at 40 °C	ISO 3104	mm ² /s	10
Pour point	ISO 3016	°C	- 63
Flash point (closed cup)	ISO 2719	°C	145
Dielectric strength: untreated oil	IEC 156	kV	40 - 60
Dielectric strength: oil after drying and filtering	IEC 296	kV	70
Corrosive sulfur	ASTM D 1275B	-	non corrosive
Corrosive sulfur	IEC 62535	-	non corrosive
Corrosive sulfur	DIN 51353	-	non corrosive
Inhibitors	IEC 60666	%	0.37

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS
Industrie & Spécialités
07-02-2020 (supersedes 19-03-2018)
ISOVOLTINE II X
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded from www.quick-fds.com.