



VULTREX™ API MODIFIED COMPOUND

Introduction

Petro-Canada Lubricants' VULTREX API Modified Thread Compound is a specially formulated lithium grease for the lubrication and sealing of thread connections in oil field applications. VULTREX API Modified Thread Compound protects the threads on casing, tubing connections and line pipe against galling during makeup and breakout. It maintains its product integrity, resisting hardening, drying out, evaporation and oxidation. This metal-based compound conforms to API RP 5A3*. *Please note: VULTREX API Modified Thread Compound is not recommended for rotary shouldered connections.*

Features and Benefits

VULTREX API MODIFIED THREAD COMPOUND PROVIDES:

- **Excellent thread protection during make-up and disassembly**
 - Reduced component damage from galling and seizure
 - Reduced torque requirements in breaking joints
- **Excellent resistance to rust and corrosion**
 - Extended thread protection and life in storage and in service which may reduce maintenance costs
 - Resists pitting and discoloration of threaded surfaces during field use and storage
 - Resists water absorption
- **Good low temperature handling properties**
 - Ease of application in cold weather
 - Suitable for wide operating temperature range

Applications

Petro-Canada Lubricants' VULTREX API Modified Thread Compound is suitable for thread protection and connection sealing in all phases of drilling in many types of oil field applications over a wide range of operating conditions.

VULTREX API Modified Thread Compound is recommended for use on the threads of round casings, buttress casings, tubing connections and line piping. It can withstand high pressures (up to 10,000 psi) and can prevent leakage at temperatures greater than 149°C/300°F.

It is not recommended for use on rotary shouldered connections. Do not use VULTREX API Modified Thread Compound on oxygen lines or in oxygen enriched atmospheres.

*American Petroleum Institute Recommended Practice 5A3: "Recommended Practice on Thread Compounds for Casing, Tubing and Line Pipe": 2nd Ed., July 2003.

Typical Performance Data

PROPERTY	TEST METHOD	VULTREX API MODIFIED THREAD COMPOUND
Appearance	Visual	Dark copper
Dropping Point, °C / °F	D2265	177 / 350
Worked Penetration @ 25°C	D217	328
Soap Type		Lithium
Copper Corrosion	D4048	1b
Brushing Ability @ -18°C (-1°F)	API RP 5A3	Pass
Evaporation, % vol fraction loss, 24 h, 100°C	API RP 5A3	≤ 0.5
Gas evolution, cm ³ , 120 h, 66°C	API RP 5A3	-2
Oil separation, % vol fraction, 24 h, 100°C	API RP 5A3	< 4.0
Water leaching, % mass fraction loss, 2h, 66°C	API RP 5A3	< 1.0

The values quoted above are typical of normal production. They do not constitute a specification.

Note that all connection contact surfaces should be clean and free of moisture and contaminants prior to the application of the thread compound to prevent grease compatibility issues.

To order product or to learn more about how Petro-Canada Lubricants can help your business visit: **lubricants.petro-canada.com** or contact us at: **lubecsr@petrocanadalsp.com**



IM-7922E (2019.06)

™ Owned or used under license.



Beyond today's standards.™