





RAVENOL SCOOTER 2-Takt Mineral



And the State of t

ART.-NR. 1153150

1 L | 1153150-001 4 L | 1153150-004 10 L | 1153150-010 20 L | 1153150-020 20 L | 1153150-B20 1000 L | 1153150-700 SPECIFICATIONS API TB |ISO-L-EGB
APPROVALS JASO FB (049RAV156)
RECOMMENDATIONS APRILIA | HONDA | SUZUKI | YAMAHA | KYMCO |
PEUGEOT | PIAGGIO | VESPA

RAVENOL SCOOTER 2-Takt Mineral is high quality mineral two-stroke engine oil.

RAVENOL SCOOTER 2-Takt Mineral is formulated with mineral base oils with effectively additives for optimum protection against wear and prevent corrosion, deposits and auto-ignitions. RAVENOL SCOOTER 2-Takt Mineral is optimized for air- and watercooled two stroke engines.

Application Notes

RAVENOL SCOOTER 2-Takt Mineral can generally be mixed with regular petrol 1:50.

RAVENOL SCOOTER 2-Takt Mineral is best choice for separate lubrication and self-mixing systems. The use in oil injection systems this product will ensure optimum lubrication and minimizes smoke environmentally friendly.

RAVENOL SCOOTER 2-Takt Mineral is used for lubrication of air-cooled two-stroke petrol engines.

RAVENOL SCOOTER 2-Takt Mineral is also suitable for the lubrication of two stroke scooters with water cooling. Suitable for separate lubrication systems and self-mixing systems.

Characteristics

RAVENOL SCOOTER 2-Takt Mineral offers:

- A proper lubrication of all engine parts
- A strong cleaning effect, for clean combustion chambers. Cleans intake and exhaust ports from combustion residues and deposits
- Clean spark plugs provide optimal performance of the engines
- A very high wear and corrosion protection
- Low exhaust emission levels by good combustion
- Immediate, homogeneous mixture with the used fuel (including lead-free)







| Property | Unit | Data | Audit |
|--------------------|-------|------|--------------|
| Density at 20°C | kg/m³ | 882 | EN ISO 12185 |
| Colour | | rot | visual |
| Viscosity at 100°C | mm²/s | 8,7 | DIN 51 562 |
| Viscosity at 40°C | mm²/s | 70,0 | DIN 51 562 |
| Viscosity index VI | | 100 | DIN ISO 2909 |
| Pourpoint | °C | -24 | DIN ISO 3016 |
| Flash point (COC) | °C | 190 | DIN ISO 2592 |

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 16. March 2021