



RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth.



VISCOSITY 20W-50

SPECIFICATIONS JASO MA2

FABRICATION FULLY SYNTHETIC

RECOMMENDATIONS MOTO GUZZI MOTORCYCLES | VICTORY MOTORCYCLES | BMW CRUISER MOTORCYCLES | HARLEY DAVIDSON 62600005, 62600031 | HONDA 08C35-A251M01, 08C35-A251L01 | YAMALUBE LUB20W50AP04, LUB20W50AP12 | TRIUMPH MOTORCYCLES | SUZUKI V-TWIN MOTOR OIL | INDIAN MOTORCYCLES

ART.-NR. 1171105

1 L | 1171105-001
4 L | 1171105-004
20 L | 1171105-020
20 L | 1171105-B20
208 L | 1171105-208
208 L | 1171105-D28
1000 L | 1171105-700

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is a high grade, fully-synthetic 3-in-1 lubricant for engine, drive and crank shaft, that was specially designed for cruiser and chopper motorcycles. Thanks to its synthetic components and specifically attuned, innovative additives, it is excellently suited for the demanding engines, drives and crankshafts of cruise and chopper motorcycles.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. reduces the friction and reliably protects the valves and the crankshaft against metal-to-metal contact. The consistent viscosity reduces load peaks at high temperatures.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. demonstrates excellent stability and durability against thermal loads under extremely high temperatures that can occur in air-cooled V-twin engines.

Application Notes

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is suitable as an engine oil for all V-twin chopper und cruiser motorcycles if the specification SAE 20W-50 is required.

Characteristics

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. offers:

- a very stable and outstanding viscosity behaviour
- reduced friction
- outstanding viscosity temperature characteristics
- a reliable lubrication film at extremely high operating temperatures
- very good protection against wear and corrosion
- protection against foaming
- excellent deterging and dispersing properties



Property	Unit	Data	Audit
Density at 20°C	kg/m ³	858	EN ISO 12185
Colour		braun	visual
Viscosity at 100°C	mm ² /s	19.8	DIN 51 562
Viscosity at 40°C	mm ² /s	139.67	DIN 51 562
Viscosity at -15°C	mPa*s	4473	ASTM D5293
Viscosity index VI		163	DIN 51 562
Pourpoint	°C	-42	DIN ISO 3016
Flash point (COC)	°C	252	DIN ISO 2592
TBN	mg KOH/g	7,4	ASTM D2896

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 28. November 2019