



RAVENOL QUAD 4T SAE 10W-40



VISCOSITY 10W-40

SPECIFICATIONS API SL

FABRICATION SEMI-SYNTHETIC

APPROVALS JASO MA2 T 903:2011

RECOMMENDATIONS 4-STROKE QUAD ENGINES FROM KAWASAKI, YAMAHA, BOMBARDIER, SUZUKI, HONDA

ART.-NR. 1152160

1 L | 1152160-001
4 L | 1152160-004
20 L | 1152160-020
20 L | 1152160-B20
1000 L | 1152160-700

RAVENOL QUAD 4T SAE 10W-40 4-stroke motor oil is especially developed for quads and ATVs (all-terrain vehicles). It is used in 4-stroke quad engines from KAWASAKI, YAMAHA, BOMBARDIER and SUZUKI. Special EP additives reliably protect the transmission system against wear and facilitate start-up when in gear as well as the process of changing gears. The smooth-running viscosity of **RAVENOL QUAD 4T SAE 10W-40** allows for a low-wear cold start even in extremely low outdoor temperatures.

Even in low gears and under extremely high loads **RAVENOL QUAD 4T SAE 10W-40** ensures a strong lubricant film and protects against wear. Special EP additives reliably protect the transmission system against wear, facilitate start-up when in gear as well as the process of changing gears. Compatible with wet clutch system and catalytic converters.

Can be used all year round. Low tendency to evaporation and therefore, low oil consumption.

Application Notes

RAVENOL QUAD 4T SAE 10W-40 is used for 4-stroke quad engines from leading manufacturers. Compatible with wet clutch system and catalytic converters.

RAVENOL QUAD 4T SAE 10W-40 is an all season motor oil.

Characteristics

RAVENOL QUAD 4T SAE 10W-40 offers:

- Low-wear cold start even at extremely low outdoor temperatures
- A strong lubricant film and high wear protection
- Compatibility with wet clutch systems and catalytic converters
- All season application
- High corrosion and wear protection
- Low tendency to evaporation and therefore, low oil consumption



Property	Unit	Data	Audit
Density at 20°C	kg/m ³	862	EN ISO 12185
Colour		grün	visual
Viscosity at 100°C	mm ² /s	13,9	DIN 51 562
Viscosity at 40°C	mm ² /s	93,2	DIN 51 562
Viscosity index VI		151	DIN ISO 2909
Pourpoint	°C	-36	DIN ISO 3016
Flash point (COC)	°C	238	DIN ISO 2592
TBN	mg KOH/g	9,8	ASTM D2896
Sulphated ash	%wt.	1,5	DIN 51 575

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 27. July 2020