





RAVENOL Kompressoren-Oel VDL 100



ART.-NR. 1330100

10 L | 1330100-010 20 L | 1330100-020 20 L | 1330100-B20 1000 L | 1330100-700 SPECIFICATIONS VBL, VCL RECOMMENDATIONS ATLAS COPCO | AUDI | ALUP | COMPAIR | FIAC | FINI | KAESER

RAVENOL Kompressorenöl VDL 100 meets the high requirements of DIN 51506. Specially designed with high quality, age-resistant base oils.

RAVENOL Kompressorenöl VDL 100 has a good adhesion, is water repellent and wear reducing. As many compressors operate at high temperatures, the oil should have good aging resistance at very low residue formation.

RAVENOL Kompressorenöl VDL 100 provides a secure lubrication not only in the upper temperature range, also in the cold state of the compressor to achieve a reduction of wear. By selected and coordinated additive composition the tendency to coking and the formation of flammable residues is minimized.

Application Notes

RAVENOL Kompressorenöl VDL 100 can be used in stationary and mobile compressors with discharge temperatures up to 220°C.

RAVENOL Kompressorenöl VDL 100 can also be used for lubrication of engines and diesel engines where the manufacturer does not stipulate any HD motor oil.

Characteristics

RAVENOL Kompressorenöl VDL100 offers:

- Excellent aging resistance
- Best wear protection
- Excellent viscosity-temperature behavior
- Very good cold starting properties
- Low coking tendency

| Property | Unit | Data | Audit |
|--------------------|-------|-----------|--------------|
| Density at 20°C | kg/m³ | 866 | EN ISO 12185 |
| Colour | | gelbbraun | visual |
| Viscosity at 100°C | mm²/s | 11,2 | DIN 51 562 |

- Certificate / Product Information -





| Property | Unit | Data | Audit |
|--------------------|-------|-------|--------------|
| Viscosity at 40°C | mm²/s | 100,2 | DIN 51 562 |
| Viscosity index VI | | 97 | DIN ISO 2909 |
| Pourpoint | °C | -22 | DIN ISO 3016 |
| Flash point (COC) | °C | 235 | DIN ISO 2592 |

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 24. January 2020