



RAVENOL Hot Red Grease HRG 2



ART.-NR. 1340121

1 Kg | 1340121-001
5 Kg | 1340121-005
10 Kg | 1340121-010
15 Kg | 1340121-015
25 Kg | 1340121-025
100 g | 1340121-100
180 Kg | 1340121-180
200 g | 1340121-200
400 g | 1340121-400

SPECIFICATIONS DIN 51 502: KP2P-35 | ISO 6743 PART 9: ISO-L-XCEEB2
APPROVALS MAN 284 LI-H2 | MB-APPROVAL 265.1

RAVENOL Hot Red Grease HRG 2 is a red lithium complex soap lubricating grease on the basis of high quality base oils. Excellent walk stability, rust and corrosion protection. Application for the lubrication of roller and friction bearings under extreme pressure at high bearing temperatures. Particularly recommended for the lubrication of wheel bearings on commercial vehicles and for high-speed passenger car wheel bearings.

Application Notes

RAVENOL Hot Red Grease HRG 2 is used for the lubrication of roller and friction bearings under extreme pressure at high bearing temperatures.

RAVENOL Hot Red Grease HRG 2 is particularly recommended for the lubrication of commercial vehicles and for high-speed passenger car wheel bearings.

Characteristics

RAVENOL Hot Red Grease HRG 2 offers:

- Walk stability
- Resistance to oxidation
- Water resistance
- Good corrosion protection characteristics
- High thermal load capacity
- High pressure susceptibility



- Good adhesion

Property	Unit	Data	Audit
Colour		rot	visual
Thickener		Lithium-Komplexseifen	-
NLGI-Class		2	DIN 51 818
DIN-Product-Classification		KP2P-35	DIN 51 502
ISO-Product-Classification		ISO-L-XCEEB2	ISO 6743 P.9
Working Temperature	°C	-35/+160	DIN 51 825
Short Term up to	°C	200	-
Worked Penetration 60 strokes	mm/10 bei 25°C	265-295	ISO 2137
Corrosion (SKF Emcors dist. Water)	Corr. Degree	0	DIN 51 802
Dropping Point	°C	>260	DIN ISO 2176
Copper Corrosion (24h/120°C)		1	DIN 51 811
Water Resistance (3h/90°C)	°C	1-90	DIN 51 807 T.1
VKA Pressure Carrying Capacity	N	2600-2800	DIN 51 350 T.4
Kinematic Viscosity (Base Oil)	mm ² /s bei 40°C	140	DIN 51562-1

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 22. August 2016